





## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification 7 :</b> <b>C07C 69/92, C09K 19/20, 19/34, 19/32, 19/38</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 00/55110</b> <b>(43) International Publication Date:</b> 21 September 2000 (21.09.00)
<b>(21) International Application Number:</b> PCT/IB00/00158 <b>(22) International Filing Date:</b> 15 February 2000 (15.02.00) <b>(30) Priority Data:</b> 9906168.1 17 March 1999 (17.03.99) GB <b>(71) Applicant (for all designated States except US):</b> ROLIC AG [CH/CH]; Innere Guterstrasse 2, CH-6301 Zug (CH). <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> LUKAC, Teodor [CH/CH]; Oberwilerstrasse 66, CH-4054 Basel (CH). BENECKE, Carsten [DE/DE]; Vierthauen 9, D-79576 Weil Am Rhein (DE). BUCHECKER, Richard [CH/CH]; 12A Felsenstrasse, CH-8008 Zurich (CH). <b>(74) Agent:</b> ENGLAND, Christopher, David; BTG International Limited, 10 Fleet Place, Limeburner Lane, London EC4M 7SB (GB).		<b>(81) Designated States:</b> AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>

(54) Title: LIQUID CRYSTAL COMPOUNDS



(I)



(II)

## (57) Abstract

A compound of formula (I), wherein  $G^1$  and  $G^2$  independently represent a polymerisable mesogenic residue; X represents a group selected from  $-\text{CH}_2-$ ,  $-\text{O}-$ ,  $-\text{CO}-$ ,  $-\text{COO}-$ ,  $-\text{OOC}-$ ,  $-\text{CONR}'-$ ,  $-\text{OCOO}-$ ,  $-\text{OCONR}'-$ ; Sp represents a group of the formula  $-(\text{CH}_2)_p-$  in which p is an integer of 1 to 18 and in which one or two non adjacent  $-\text{CH}_2-$  groups are optionally replaced by  $-\text{CH}=\text{CH}-$ ; or in which one or two  $-\text{CH}_2-$  groups are optionally replaced by one or two groups selected from the group consisting of  $-\text{O}-$ ,  $-\text{CO}-$ ,  $-\text{COO}-$ ,  $-\text{OOC}-$ ,  $-\text{CONR}'-$ ,  $-\text{OCOO}-$ ,  $-\text{OCONR}'-$  with the proviso that firstly the spacer group does not contain two adjacent heteroatoms and secondly when X is  $-\text{CH}_2-$ , p can also have a value of 0; and M represents an achiral group of formula (II) in which A and B independently represent an optionally substituted six membered isocyclic or heterocyclic group or naphthalenediyl; C is selected from the group consisting of an optionally substituted five and six membered isocyclic or heterocyclic group or naphthalenediyl;  $n^1$  and  $n^2$  are 0 or 1 with the proviso that firstly  $1 \leq n^1 + n^2 \leq 2$  and secondly, when C is naphthalenediyl  $0 \leq n^1 + n^2 \leq 2$ ;  $Z^1$  is selected from the group consisting of  $-\text{O}-$ ,  $-\text{COO}-$ ,  $-\text{OOC}-$ ,  $-\text{CO}-$ ,  $-\text{CONR}'-$ ,  $-\text{NR}'\text{CO}-$ ,  $-\text{OCOO}-$ ,  $-\text{OCONR}'-$ ,  $-\text{NR}'\text{COO}-$  and a single bond; in which  $R'$  is selected from the group consisting of hydrogen, a lower achiral alkyl group and a lower achiral alkenyl group;  $Z^2$  and  $Z^3$  are independently selected from the group consisting of single bond,  $-\text{COO}-$ ,  $-\text{OOC}-$ ,  $-\text{CH}_2\text{CH}_2-$ ,  $-\text{CH}_2\text{O}-$ ,  $-\text{OCH}_2-$ ,  $-\text{CH}=\text{CH}-$ ,  $-\text{C}\equiv\text{C}-$ ,  $-(\text{CH}_2)_4-$  and  $-(\text{CH}_2)_3\text{O}-$ ; and  $R^1$  is selected from the group consisting of  $-\text{CN}$ ,  $-\text{COR}$ ,  $-\text{COOR}$ ,  $-\text{OCOR}$ ,  $-\text{CONR}'\text{R}$ ,  $-\text{NR}'\text{COR}$ ,  $-\text{OCOOR}$ ,  $-\text{OCONR}'\text{R}$ ,  $-\text{NR}'\text{COOR}$ ,  $-\text{F}$ ,  $-\text{Cl}$ ,  $-\text{CF}_3$ ,  $-\text{OCF}_3$ ,  $-\text{OR}$  and  $-\text{R}$  in which R is selected from the group consisting of hydrogen, an achiral  $\text{C}_{1-18}$  alkyl group and an achiral  $\text{C}_{4-18}$  alkenyl group with the double bond at 3-position or higher; and  $R'$  is as defined above; with the proviso that at most one of the rings A, B and C is a naphthalenediyl group is provided as well as liquid crystalline mixtures, films and electro-optical devices comprising the compound.

*FOR THE PURPOSES OF INFORMATION ONLY*

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

**BEST AVAILABLE COPY**

## Liquid Crystal Compounds

The present invention relates to laterally substituted curable Liquid Crystals (LCPs) having mesogenic properties or properties which cause these LCPs to be compatible with a mesogenic molecular structure. In particular the present invention  
5 relates to laterally substituted curable Liquid Crystals (LCPs) with adjustable optical anisotropy and in parallel with low melting point or good supercoolability, relatively high clearing point and good alignment properties and the use of such LCPs in the preparation of substantially uniform or patterned film in which the orientation of the LCP molecules in the plane and relative to the plane of the substrate can be  
10 controlled.

Films prepared from curable Liquid Crystals (LCP films) are well known to a skilled person and are used in the preparation of optical and electro-optical devices. US 5,650,534 discloses compounds and mixtures used to prepare components suitable for use non-linear optical (NLO) applications. These compounds are optically active  
15 and exhibit chiral smectic or chiral nematic mesophases. US 5,707,544 also discloses compounds and mixtures suitable for use in NLO applications. However, these compounds are characterised by relatively high melting points. US 5,593,617 discloses photochemically polymerisable liquid crystal compounds and mixtures, which are used to prepare optical and electronic components. However, these  
20 mixtures have a relatively narrow operating range and are unsuitable for use at higher temperatures.

LCP films are generally manufactured by using known coating techniques such as spin coating. This involves casting an organic solution of a cross-linkable LCP or LCP mixture onto a substrate provided with an orientation layer. The organic  
25 solvent is subsequently removed to give a well-oriented, solvent-free mesogenic LCP layer, which in turn is cross-linked to give an LCP film. The desired optical performance of such films depends crucially on some reproducible physical parameters which the LCP material has to fulfil simultaneously. Such properties are a nematic mesophase, a high clearing point, a low melting point or a low tendency to


crystallise when cooled below melting point (supercooling), good solubility in organic solvents, good miscibility with other LCPs, good aligning properties on orientation layers, and the ability to form an adjustable tilt out of the substrate plane essentially free of tilt domains and disclinations. Tilt domains are regions within the LCP film in which the long axes of the LCP molecules form tilt angles out of the plane of the substrate of the same size but in opposite direction. Disclinations are borderlines of neighbouring tilt domains where LCP molecules of opposite tilt angles are adjacent. These tilt domains and disclinations result in both a disturbance in the uniform appearance of the film and an inhomogeneous optical performance.

Good aligning properties and the ability to form an adjustable tilt angle are of particular relevance if photo-orientated and photo-patterned orientation layers are used for the orientation of LCPs. This so-called linear photo-polymerisation (LPP) technology (cf. e.g. *Nature*, 381, p. 212 (1996)) allows the production of not only uniform but also structured (photo-patterned) orientation layers. If such structured orientation layers are used for the orientation of LCPs, the LCP molecules should adapt the information given by the orientation layer with respect to the direction of alignment and the tilt angle.

For adjusting the optical properties of the layers and films prepared from LCPs as for example retardation films, it is further essential to have available a variety of LCP materials with differing optical anisotropy, mainly high optical anisotropy. It is known that LCPs exhibiting a high optical anisotropy often show a negative impact on several of the above properties. Particularly the formation of smectic mesophases, high melting points, an enhanced tendency to crystallise, a low solubility in organic solvents or reduced miscibility with other LCPs is observed. Furthermore the ability of homogeneous alignment free of tilt domains and disclinations is often reduced.

There is, therefore, a need for a new LCP material that may be used in the preparation of an LCP mixture, which significantly reduces the aforementioned disadvantages. The present invention addresses that need.

A first aspect of the invention provides a compound of formula (I)



I


wherein

$G^1$  and  $G^2$  independently represent a polymerisable mesogenic residue;

5  $X$  represents a group selected from  $-CH_2-$ ,  $-O-$ ,  $-CO-$ ,  $-COO-$ ,  $-OOC-$ ,  $-CONR'-$ ,  $-OCOO-$ ,  $-OCONR'$ ;

$Sp$  represents a group of the formula  $-(CH_2)_p-$  in which  $p$  is an integer of 1 to 18 and in which one or two non adjacent  $-CH_2-$  groups are optionally replaced by  $-CH=CH-$ ; or in which one or two  $-CH_2-$  groups are optionally replaced by one or two groups selected from the group consisting of  $-O-$ ,  $-CO-$ ,  $-COO-$ ,  $-OOC-$ ,  $-CONR'-$ ,  $-OCOO-$ ,  $-OCONR'$  with the proviso that firstly the spacer group does not contain two adjacent heteroatoms and secondly when  $X$  is  $-CH_2-$ ,  $p$  can also have a value of 0; and

15  $M$  represents an achiral group of formula (II)



in which

20  $A$  and  $B$  independently represent a six membered isocyclic or heterocyclic group or naphthalenediyl;

$C$  is selected from the group consisting of a five and six membered isocyclic or heterocyclic group or naphthalenediyl;

$n^1$  and  $n^2$  are 0 or 1 with the proviso that firstly  $1 \leq n^1 + n^2 \leq 2$  and secondly, when  $C$  is naphthalenediyl  $0 \leq n^1 + n^2 \leq 2$ ;

- $Z^1$  is selected from the group consisting of -O-, -COO-, -OOC-, -CO-, -CONR'-, -NR'CO-, OCOO-, -OCONR'-, -NR'COO- and a single bond;  
in which
- 5  $R'$  is selected from the group consisting of hydrogen, a lower achiral alkyl group and a lower achiral alkenyl group;
- $Z^2$  and  $Z^3$  are independently selected from the group consisting of single bond, -COO-, -OOC-, -CH<sub>2</sub>-CH<sub>2</sub>-, -CH<sub>2</sub>O-, -OCH<sub>2</sub>-, -CH=CH-, -C≡C-, -(CH<sub>2</sub>)<sub>4</sub>- and -(CH<sub>2</sub>)<sub>3</sub>O-; and
- 10  $R^1$  is selected from the group consisting of -CN, -COR, -COOR, -OCOR, -CONR'R, -NR'COR, OCOOR, -OCONR'R, -NR'COOR, -F, -Cl, -CF<sub>3</sub>, -OCF<sub>3</sub>, -OR and -R  
in which
- 15  $R$  is selected from the group consisting of hydrogen, an achiral C<sub>1-18</sub> alkyl group and an achiral C<sub>4-18</sub> alkenyl group with the double bond at 3-position or higher; and  
 $R'$  is as defined above;
- with the proviso that at most one of the rings A, B and C is a naphthalenediyl group.
- 20 In addition to the laterally substituted mesogenic compounds referred to above, such compounds are also disclosed in WO 95/24454 and WO 95/24455. However, many of these compounds are not suitable for preparing LCP films with high optical anisotropy without one or more of the aforementioned disadvantages. It has been found that by using the compounds of the present invention it is possible to
- 25 control the optical anisotropy of LCPs without significant increase of melting point or decrease of clearing point. In addition they generally have a surprisingly low tendency to crystallise even far below the melting point (good supercoolability). Furthermore they generally exhibit enhanced alignment properties especially on structured LPP orientation layers, they are able to form tilt angles and show a decreased tendency to
- 30 form tilt domains and disclinations. Furthermore the compounds of the invention have

a comparatively good solubility in organic solvents and a high miscibility with other LCP compounds.

The optical anisotropy of the compounds of the invention may be easily adapted to requirements only by selecting different groups of M of formula I without  
5 changing the main core of the molecule. This allows an economical access to a broad range of LCPs exhibiting different optical anisotropies with a minimum of chemical steps in their production.

The polymerisable mesogenic residues  $G^1$  and  $G^2$  may be the same or different, but are preferably the same.

10 The group X is preferably selected from the group consisting of  $-CH_2-$ ,  $-O-$ ,  $-COO-$  and  $-OOC-$ .

The spacer group Sp may be optionally substituted by one or more fluorine or chlorine atoms. Groups in which there are no substituent groups present are preferred. It is especially preferred that the integer p has a value of from 1 to 12 and that no  
15 more than two  $-CH_2-$  groups are replaced by  $-O-$  and that no more than one  $-CH_2-$  group is replaced by one group selected from the group consisting of  $-CH=CH-$ ,  $-CO-$ ,  $-COO-$ ,  $-OOC-$ ,  $-CONR'-$ ,  $-OCOO-$  and  $-OCONR'$ .

The groups A and B comprising the achiral group M are either saturated, unsaturated or aromatic. They are optionally substituted by one or two substituents  
20 selected from the group consisting of F, Cl, CN, a lower alkyl, lower alkenyl, lower alkoxy and lower alkenyloxy. Preferably the groups A and B each contain no more than one substituent. It is especially preferred that the groups A and B contain no substitution.

It is preferred that the groups A and B are selected from the group consisting  
25 of 1,4-phenylene, pyridine-2,5-diyl, pyrimidine-2,5-diyl, trans-1,4-cyclohexylene or trans-1,3-dioxane-2,5-diyl, 1,4-naphthalenediyl and 2,6-naphthalenediyl. It is especially preferred that A and B are selected from the group consisting of 1,4-phenylene, trans-1,4-cyclohexylene and 2,6-naphthalenediyl.

The group C comprising the achiral group M is either saturated, unsaturated or  
30 aromatic. It is optionally substituted with one or two substituents selected from the

group consisting of F, Cl, CN, a lower alkyl, lower alkenyl, lower alkoxy and lower alkenyloxy. It is preferred that the group C contains at most one substituent. It is especially preferred that the group C contains no substitution.

It is preferred that the group C is selected from furan-2,4-diyl, furan-2,5-diyl, 5 tetrahydrofuran-2,4-diyl, tetrahydrofuran-2,5-diyl, dioxolane-2,4-diyl, dioxolane-2,5-diyl, oxazole-2,4-diyl, oxazole-2,5-diyl, cyclopentane-1,3-diyl, cyclopentane-1,4-diyl, 1,4-phenylene, pyridine-2,5-diyl, pyrimidine-2,5-diyl, trans-1,4-cyclohexylene or dioxane-2,5-diyl, 1,4-naphthalenediyl and 2,6-naphthalenediyl. It is especially preferred that C is selected from the group consisting 10 of furan-2,5-diyl, tetrahydrofuran-2,5-diyl, oxazole-2,5-diyl, 1,4-phenylene, trans-1,4-cyclohexylene, and 2,6-naphthalenediyl.

The group  $Z^1$  comprising the achiral group M is preferably selected from the group consisting of -O-, -COO-, -OOC- and a single bond. It is especially preferred that  $Z^1$  is selected from -O- or a single bond.

15 The groups  $Z^2$  and  $Z^3$  comprising the achiral group M are preferably selected from the group consisting of -COO-, -OOC-, -CH<sub>2</sub>CH<sub>2</sub>-, -CH<sub>2</sub>O-, -OCH<sub>2</sub>-, -CH=CH-, -C≡C- and a single bond. It is especially preferred that  $Z^2$  and  $Z^3$  are selected from the group consisting of -COO-, -OOC-, -C≡C- and a single bond.

The group  $R^1$  comprising the achiral group M is preferably selected from the 20 group consisting of -CN, -COOR, -OCOR, F, Cl, CF<sub>3</sub>, OCF<sub>3</sub>, OR, R, in which R represents a C<sub>1-12</sub> achiral alkyl, C<sub>4-12</sub> achiral alkenyl group with the double bond at position 3- or higher, or hydrogen. It is especially preferred that  $R^1$  is selected from the group consisting of -CN, F, Cl, CF<sub>3</sub>, OCF<sub>3</sub>, OR, R, in which R represents a C<sub>1-8</sub> achiral alkyl group or hydrogen.

25 By the term "lower alkyl" it should be understood to include a C<sub>1-6</sub> achiral, branched or straight-chained alkyl group. Examples of lower alkyl groups that may be present in the compounds of the invention include methyl, ethyl, propyl, butyl, pentyl hexyl and the like.

By the term "lower alkenyl" it should be understood to include C<sub>3-6</sub> achiral, 30 branched or straight-chained alkenyl group in which the double bond is at position




2- or higher. Examples of lower alkenyl groups that may be present in the compounds of the invention include 2-propenyl, 3-butenyl, 3-isopentenyl, 4-pentenyl, 5-hexenyl, 4-isohexenyl and the like.

By the term "lower alkoxy" it should be understood to include C<sub>1-6</sub> achiral, branched or straight-chained alkoxy group. Examples of lower alkoxy groups that may be present in the compounds of the invention include methoxy, ethoxy, propoxy, butoxy, pentoxy hexoxy and the like.

By the term "alkenyloxy" it should be understood to include C<sub>3-6</sub> achiral, branched or straight-chained alkenyloxy group in which the double bond is at position 2- or higher. Examples of lower alkenyloxy groups that may be present in the compounds of the invention include 2-propenyloxy, 3-butenyloxy, 4-pentenyl, 5-hexenyloxy and the like.

Preferably the polymerisable mesogenic residues G<sup>1</sup> and G<sup>2</sup> are each independently represented by the group of formula III



III

wherein

D and E are independently selected from the group consisting of 1,4-phenylene, pyridine-2,5-diyl, pyrimidine-2,5-diyl, trans-1,4-cyclohexylene and trans-1,3-dioxane-2,5-diyl;

m is 1 or 0,

Z<sup>4</sup> and Z<sup>5</sup> are independently selected from the group consisting of a single bond, -COO-, -OOC-, -CH<sub>2</sub>-CH<sub>2</sub>-, -CH<sub>2</sub>O-, -OCH<sub>2</sub>-, -CH=CH-, -C≡C-, -(CH<sub>2</sub>)<sub>4</sub>- and -(CH<sub>2</sub>)<sub>3</sub>O-;

$Z^6$  represent a group of formula  $-(CH_2)_pX-$  in which  $p$  is an integer having a value of 1 to 18 and  $X$  is defined above, and in which one or two non adjacent  $-CH_2-$  groups may be optionally replaced by  $-CH=CH-$  or in which one or two  $-CH_2-$  groups may be replaced by one or two additional linking groups  $X$  with the proviso that firstly the group  $Z^6$  does not contain two adjacent heteroatoms and secondly when  $X$  is  $-CH_2$ ,  $p$  can also have a value of 0

$R^2$  represents a polymerisable group selected from the group consisting of  $CH_2=C(Ph)-$ ,  $CH_2=CW-COO-$ ,  $CH_2=CH-COO-Ph-$ ,  $CH_2=CW-CO-NH-$ ,  $CH_2=CH-O-$ ,  $CH_2=CH-OOC-$ ,  $Ph-CH=CH-$ ,  $CH_2=CH-Ph-$ ,  $CH_2=CH-Ph-O-$ ,  $R^3-Ph-CH=CH-COO-$ ,  $R^3-OOC-CH=CH-Ph-O-$  and 2-W-epoxyethyl in which

$W$  represents H, Cl, Ph or a lower alkyl,  $R^3$  represents a lower alkyl with the proviso that when  $R^3$  is attached to a phenylene group ( $-Ph-$ ) it may also represent hydrogen or a lower alkoxy.

The terms "Ph" and "Ph-" will be understood to indicate a phenyl group. The term " $-Ph-$ " will be understood to mean any isomer of phenylene, namely 1,2-phenylene, 1,3-phenylene or 1,4-phenylene, except where the context requires otherwise.

The groups D and E are optionally substituted with one or two halogens,  $-CN$ , lower alkyl, lower alkenyl, lower alkoxy or lower alkenyloxy groups. If halogen substituents are present they are preferably F or Cl. It is preferred that the groups D and E are selected from optionally substituted 1,4-phenylene and 1,4-cyclohexylene rings. It is especially preferred that the groups D and E contain no substitution.

It is preferred that the groups  $Z^4$  and  $Z^5$  are selected from the group consisting of a single bond,  $-COO-$ ,  $-OOC-$ ,  $-CH_2-CH_2-$ ,  $-CH_2O-$ ,  $-OCH_2-$ ,  $-CH=CH-$  and

-C≡C-. It is especially preferred that  $Z^4$  and  $Z^5$  represent a single bond, -C≡C-, -COO- or -OOC-.


5  $Z^6$  may be optionally substituted by one or more halogen atoms, preferably one or more fluorine atoms. It is preferred that p has a value of 1 to 11. It is also preferred that  $Z^6$  contains no substitution. It is further preferred that, for the group  $Z^6$ , X is selected from -CH<sub>2</sub>-, -O-, -COO- and -OOC-, especially -CH<sub>2</sub>- or -O-.

It is preferred that the group  $R^2$  is selected from the group consisting of CH<sub>2</sub>=CW-COO- and CH<sub>2</sub>=CH-O-.


10 It is preferred that the sum of the two integers m for each of the groups  $G^1$  and  $G^2$  is 0 or 1. It is especially preferred that for both  $G^1$  and  $G^2$  m has a value of 0.

The compounds of the invention may be readily prepared using procedures well known to a skilled person in accordance with any one of the procedures set out in Schemes 1 and 2 below.

## Scheme 1



## Scheme 2



in which :

DEAD is diethyl azodicarboxylate

TPP is triphenylphosphine

THF is tetrahydrofuran

KI is potassium iodide

DBU is 1,8-diazabicyclo[5.4.0]undec-7-ene

5 EDC is N-(3-dimethylaminopropyl)-N'-ethylcarbodiimide hydrochloride

DMAP is 4-dimethylaminopyridine






Suitable starting materials used in the preparation of the compounds of the present invention include, amongst others, phenyl and biphenyl alcohol and  
10 carboxylic acid compounds as well as 1,4-cyclohexanedione. The starting materials are commercially available or may be readily prepared and are well known to a skilled person.


The compounds of the invention are preferably prepared by forming a ring that includes a lateral group prior to linking the mesogenic residues. Alternatively, the  
15 compounds may be prepared by forming a ring that includes a polymerisable mesogenic residue prior to linking the lateral group. A second aspect of the invention therefore provides a method of preparation of a compound of formula (I), the method comprising forming a ring that includes a lateral group and subsequently linking the mesogenic residue thereto. The mesogenic residues  $G^1$  and  $G^2$  are preferably  
20 connected to the central ring simultaneously. As indicated above, it is especially preferred that the mesogenic residues  $G^1$  and  $G^2$  are identical.

It will be appreciated that the compounds of the invention may be used in the preparation of liquid crystalline mixtures. Such mixtures may be prepared by admixing a compound of formula (I) with one or more additional components. An  
25 organic solvent may also be used in the preparation of these mixtures. A third aspect of the invention therefore provides a liquid crystalline mixture comprising a compound of formula (I) and one or more additional components. The one or more additional components present in the liquid crystalline mixture may be further compounds of formula (I), other mesogenic compounds, compounds that are  
30 compatible with a mesogenic molecular architecture or chiral dopants for the


induction of helical pitch. The LCP mixture may also include a suitable organic solvent. Examples of solvents that may be used in the preparation of such liquid crystalline mixtures include anisole, N-methylmorpholine, caprolactone, cyclohexanone, methyl ethyl ketone and the like.

5        Examples of additional components that may be used in the preparation of liquid crystalline LCP mixtures according to the third aspect of the invention include those compounds represented by formulae III to X.






VIII




IX



X

in which

- 5  $R^4$  is selected from the group consisting of  $CH_2=CH-O-$ ,  $CH_2=CH-COO-$ ,  $CH_2=C(CH_3)-COO-$ ,  $CH_2=C(Cl)-COO-$  and



- $S^3, S^4$  independently represent  $-(CH_2)_n-$  or  $-O(CH_2)_n-$ ;  
 $E^1, E^2$  are independently selected from the group consisting of 1,4-phenylene  
 10 trans-1,4-cyclohexylene, pyridine-2,5-diyl, pyrimidine-2,5-diyl and trans 1,4-cyclohexylenc-1,4-phenylene;  
 $F^1, F^2$  are independently selected from the group consisting of 1,4-phenylene, and 2- or 3-fluoro-1,4-phenylene;  
 $L^4, L^5, L^6$  are independently selected from the group consisting of OH,  
 15  $C_1-C_{20}$ -alkyl,  $C_1-C_{20}$ -alkenyl,  $C_1-C_{20}$ -alkoxy,  $C_1-C_{20}$ -alkoxy-carbonyl, formyl,  $C_1-C_{20}$ -alkylcarbonyl,  $C_1-C_{20}$ -alkylcarbonyloxy, halogen, cyano and nitro;  
 $Z^7$  is selected from the group consisting of  $-COO-$ ,  $-OOC-$ ,  $-OCH_2-$ ,  $-CH_2O-$ ,  $-O(CH_2)_3-$ ,  $-OOC(CH_2)_2-$  and  $-COO(CH_2)_3-$ ;



- $Z^8$  is selected from the group consisting of a single bond,  $-\text{CH}_2\text{CH}_2-$ ,  $-\text{CH}_2\text{O}-$ ,  $-\text{OCH}_2-$ ,  $-\text{COO}-$ ,  $-\text{OOC}-$ ,  $-(\text{CH}_2)_4-$ ,  $-\text{O}(\text{CH}_2)_3-$ ,  $(\text{CH}_2)_3\text{O}-$  and  $-\text{C}\equiv\text{C}-$ ;
- $Z^9$  is selected from the group consisting of a single bond,  $-\text{CH}_2\text{CH}_2-$ ,  $-\text{CH}_2\text{O}-$ ,  $-\text{OCH}_2-$ ,  $-\text{COO}-$ ,  $-\text{OOC}-$ , and  $-\text{C}\equiv\text{C}-$ ;
- $Y$  is independently selected from the group consisting of hydroxy,  $\text{C}_1$ - $\text{C}_{20}$ -alkyl,  $\text{C}_1$ - $\text{C}_{20}$ -alkenyl,  $\text{C}_1$ - $\text{C}_{20}$ -alkoxy,  $\text{C}_1$ - $\text{C}_{20}$ -alkoxycarbonyl, formyl-,  $\text{C}_1$ - $\text{C}_{20}$ -alkylcarbonyl,  $\text{C}_1$ - $\text{C}_{20}$ -alkylcarbonyloxy, fluoro, chloro, bromo, cyano and nitro;
- $n$  is an integer having a value of from 2 to 20; and
- $v$  is an integer having a value of from 2 to 12

The compounds of the invention may also be used in the formation of a LCP layer by casting a LCP compound according to the first aspect of the invention or a mixture according to the third aspect of the invention onto a substrate. A fourth aspect of the invention therefore provides a method forming a LCP network comprising forming a LCP layer including a compound of formula (I) and cross-linking the layer. Liquid crystalline mixtures according to the third aspect of the invention may also be used in the manufacture of LCP networks in a similar way.

The invention also includes, in a fifth aspect of the invention, a cross-linked LCP network comprising a compound of formula (I) in a cross-linked form. Cross-linked LCP networks comprising a mixture according to the third aspect of the invention in cross-linked form may also be included in this aspect of the invention.

A sixth aspect of the invention provides the use of a compound of formula (I) in the preparation of an optical or an electro-optical device. The use, in the preparation of an optical or electro-optical device, of liquid crystalline mixtures according to the third aspect of the invention is also included in this aspect of the invention.

A seventh aspect of the invention provides an optical or an electro-optical device comprising a compound of formula (I) in a cross-linked state. An optical or


electro-optical device comprising a LCP liquid crystalline mixture in a cross-linked state according to the third aspect of the invention is also included in this aspect of the invention.

The invention will now be described with reference to the following non-limiting examples. These examples are provided by way of illustration only. Variations on these examples falling within the scope of the invention will be apparent to a skilled person.

### Examples


#### Example 1

#### Synthesis of 8-Chlorooctyl-4-(4'-octylbiphenyl) ether




A solution of diethyl azodicarboxylate (2.1g; 12mmol) tetrahydrofuran (10ml) was added dropwise at 0°C to a solution of 4-octyl-4'-hydroxybiphenyl (3.2g; 11.3mmol), 8-chlorooctanol (1.9g; 12mmol), triphenylphosphine (3.2g; 12mmol) and tetrahydrofuran (80ml) and stirred at room temperature overnight. The reaction mixture was added to water (200ml) and extracted with ethyl acetate (3 x 100ml). The combined organic layers were washed with water (2 x 100ml), dried over magnesium sulphate and filtered. The solvent was removed *in vacuo*. The residue (11.1g) was purified by flash chromatography on silica gel column using a toluene/ethyl acetate mixture (95:5) as eluent to give 4.4g (93%) of 8-Chlorooctyl-4-(4'-octylbiphenyl) ether.

#### Synthesis of 8[(4'-octyl-4-biphenylyl)oxy]octyl 2,5-dihydroxybenzoate



A mixture of 2,5-dihydroxybenzoic acid (1.7g; 11.0mmol), 1,8-diazabicyclo-  
 [5.4.0]undec-7-ene (1.7g; 11.0mmol), 8-chlorooctyl-4'-octyl-4-biphenyl ether (4.4g;  
 5 10.2mmol), potassium iodide (6.6g; 40.0mmol) and acetonitrile (150ml) was heated  
 under reflux for 72h. The reaction mixture was cooled, poured into water (600ml) and  
 extracted with ethyl acetate (3 x 150ml). The combined organic layers were washed  
 with 1N-hydrochloric acid (150ml) and water (2 x 150ml), dried over magnesium  
 sulphate and filtered. The solvent was removed *in vacuo*. The residue (4.9g) was  
 10 purified by recrystallisation from ethyl acetate/toluene to give 4.5g (80%) of  
 8-[(4'-octyl-4-biphenyl)oxy]octyl 2,5-dihydroxybenzoate.

**Synthesis of [[[8-[(4'-octyl-4-biphenyl)oxy]octyl]oxy]carbonyl]-p-phenylene  
 bis[p-[[6-(acryloyloxy)hexyl]oxy]benzoate]**




A solution of N-(3-dimethylaminopropyl)-N'-ethyl-carbodiimide hydrochloride (2.6g;  
 13.7mmol) in dichloromethane (50ml) was added slowly to a solution of 8-[(4'-octyl-  
 -4-biphenyl)oxy]octyl-2,5-dihydroxybenzoate (3.0g; 5.5mmol), 4-(6-acryloyl-  
 20 hexyloxy)benzoic acid (4.1g; 13.7mmol) and 4-dimethylaminopyridine (1.3g;  
 10.9mmol) in dichloromethane (100ml) at 0°C. The mixture was stirred at room  
 temperature overnight, added to water (200ml) and extracted with dichloromethane (3  
 x 100ml). The combined organic layers were washed with water (2 x 100ml), dried  
 over magnesium sulphate and filtered. The solvent was removed *in vacuo*. The  
 25 residue (8.4g) was purified by flash chromatography on silica gel column using a  
 toluene/ethyl acetate mixture (95:5) as eluent. Recrystallisation from ethyl

acetate/hexane gave 2.2g (38%) of  
 [[[8-[(4'-octyl-4-biphenyl)oxy]octyl]oxy]carbonyl]-p-phenylene bis[p-[[6-(acryloyl-  
 oxy)hexyl]oxy]benzoate]. Mp (C-N) = 89.5°C; Clp (N-I) = 103°C

- 5 The following compounds were synthesised using a similar method.


2,5-bis-[4-(6-acryloyloxyhexyloxy)benzoyloxy]benzoic acid 8-[4-(5-octylpyridin-  
 -2-yl)phenoxy]nonyl ester

10




Mp (C-N) = 61°C; Clp (N-I) = 89°C

- 15 [[[9-[p-(5-nonyl-2-pyrimidinyl)phenoxy]nonyl]oxy]carbonyl]-p-phenylene  
 bis[p-[[6-(acryloyloxy)hexyl]oxy]benzoate]




- 20 Mp (C-N) = 55.5°C; Clp (N-I) = 90.2°C

[[[8-[p-(trans-4-pentylcyclohexyl)phenoxy]octyl]oxy]carbonyl]-p-phenylene  
 bis[p-[[6-(acryloyloxy)hexyl]oxy]benzoate]



[[[8-[(4'-cyano-4-biphenyl)oxy]octyl]oxy]carbonyl]-p-phenylene  
bis[p-[6-(acryloyloxy)hexyl]oxy]benzoate]

5




Mp (C-N) = 72°C; Clp (N-I) = 114.7°C

Solubility in MPK: 7.2%


10

2,5-Bis[4-(6-acryloyloxyhexyloxy)benzoyloxy]benzoic acid 8-(6-pentyloxy-2-  
naphthyloxy)octyl ester




[[2-[2-[(4'-Cyano-4-biphenyl)oxy]ethoxy]ethoxy]carbonyl]-p-phenylene bis[p-  
6-(acryloyloxy)hexyloxy]benzoate

15



Mp. (C-N) = 54°C; Clp (N-I) = 86°C; Solubility in MPK: 33.2%


**2,5-Bis[4-(6-acryloyloxyhexyloxy)benzoyloxy]benzoic acid 6-[4-[(4-cyanophenyl)ethynyl]phenyloxy]hexyl ester**



5

Mp. (C-N) = 71.4°C; Clp (N-I) = 130.6°C;

**2,5-Bis[4-(6-acryloyloxyhexyloxy)benzoyloxy]benzoic acid 8-(2-naphthyloxy)octyl ester**




10

Mp. (C-N) = 63°C; Clp (N-I) = 74°C;

This compound may be supercooled

**Example 2**

**15 Synthesis of 4'-[(8-chlorooctyl)oxy]-4-biphenylol**




20

A solution of diethyl azodicarboxylate (3.5g; 20mmol) and tetrahydrofuran (10ml) was added dropwise at 0°C to a solution of 4,4'-dihydroxybiphenyl (7.4g; 40mmol), 8-chloro-1-octanol (3.3g; 20mmol), triphenylphosphine (5.2g; 20mmol) and tetrahydrofuran (120ml) and stirred at room temperature 72h. The reaction mixture was added to water (400ml) and extracted with ethyl acetate (3 x 150ml). The

combined organic layers were washed with water (2 x 150ml), dried over magnesium sulphate and filtered. The solvent was removed *in vacuo*. The residue (19.2g) was purified by flash chromatography on a silica gel column using a toluene/ethyl acetate mixture (95:5) as eluent, to give 2.6g (40%) of 4'-[(8-chlorooctyl)oxy]-4-biphenylol.

5


#### Synthesis of 4'-[(8-chlorooctyl)oxy]-4-biphenyl 2-furoate



10 A solution of 2-furoyl chloride (1.3g; 9.8mmol) was added dropwise at 0°C to a solution of 4'-[(8-chlorooctyl)oxy]-4-biphenylol (2.6g; 7.8mmol) and pyridine (20g; 253mmol), stirred at room temperature overnight. The resulting mixture was added to 1N-hydrochloric acid (200ml) and extracted with ethyl acetate (3 x 100ml). The combined organic layers were washed with saturated sodium chloride solution (2 x 80ml), dried over magnesium sulphate and filtered. The solvent was removed *in vacuo*. The residue (3.3g) was purified by recrystallisation from ethyl acetate/hexane, to give 2.9g (88%) of 4'-[(8-Chlorooctyl)oxy]-4-biphenyl-2-furoate.

15

#### Synthesis of {[8-[(2,5-dihydroxybenzoyl)oxy]octyl]oxy}-4-biphenyl 2-furoate




20

A mixture of 2,5-dihydroxybenzoic acid (1.1g; 7.0mmol), 1,8-diazabicyclo-[5.4.0]undec-7-ene (1.1g; 7.0mmol), 4'-[(8-chlorooctyl)oxy]-4biphenyl-2-furoate (2.9g; 6.8mmol), potassium iodide (5.2g; 35mmol) and acetonitrile (100ml) was heated under reflux for 48h. The cooled reaction mixture was poured into water

(500ml) and extracted with ethyl acetate (3 x 150ml). The combined organic layers were washed with 1N-hydrochloric acid (100ml) and water (2 x 100ml), dried over magnesium sulphate and filtered. The solvent was removed *in vacuo*. The residue (2.8g) was purified by flash chromatography on a silica gel column using a toluene/ethyl acetate mixture (93:7) as eluent to give 1.1g (30%) of

**Synthesis of furan-2-carboxylic acid 4'-(8-{2,5-bis-[4-(6-acryloyloxyhexyloxy)-benzoyloxy]benzoyloxy}octyloxy)biphenyl-4-yl ester**




A solution of N-(3-dimethylaminopropyl)-N'-ethyl-carbodiimide hydrochloride (1.0g; 5.1mmol) in dichloromethane (20ml) was slowly added to a solution of 4'-{8-[(2,5-dihydroxybenzoyl)oxy]octyl}oxy-4-biphenyl-2-furoate (1.1g; 2.0mmol), 4-(6-acryloyloxyhexyloxy)benzoic acid (1.5g; 5.0mmol) and 4-dimethylaminopyridine (0.5g; 3.9mmol) in dichloromethane (30ml) at 0°C. The mixture was stirred overnight at room temperature, added to water (200ml) and extracted with dichloromethane (3 x 100ml). The organic layers were washed with water (2 x 80ml), dried over magnesium sulphate and filtered. The solvent was removed *in vacuo*. The residue (2.6g) was purified by flash chromatography on a silica gel column using a toluene/ethyl acetate mixture (90:10) as eluent. Recrystallisation from ethyl acetate/isopropanol gave 0.4g (19%) of furan-2-carboxylic acid 4'-8-{2,5-bis[4-(6-acryloyloxyhexyloxy)benzoyloxy]-benzoyloxy}octyloxy)biphenyl-4-yl ester.



Mp (C-N) = 89.5°C; Clp = 103°C. The compound is supercoolable below room temperature.

5 2,5-Bis[4-(6-acryloyloxyhexyloxy)benzoyloxy]benzoic acid 8-[6-[(4-octyloxyphenyl) ethynyl]-2-naphthyloxy]hexyl ester




Mp. (C-N) = 67°C; Clp (N-I) = 145°C;

This compound may be supercooled

10


2,5-Bis[4-(6-acryloyloxyhexyloxy)benzoyloxy]benzoic acid 8-[6-[(4-cyanophenyl) ethynyl]-2-naphthyloxy]octyl ester



Mp. (C-N) = 103°C; Clp (N-I) = 142°C;

15 This compound may be supercooled

[[2-[2-[2-[(4-Cyanophenyl)ethynyl]-6-naphthyloxy]ethoxy]ethoxy]carbonyl]-p-phenylene bis[p-[6-(acryloyloxy)hexyloxy]benzoate




20

Mp. (C-N) = 90°C; Clp (N-I) = 133°C;

This compound may be supercooled

[[2-[2-[4'-[(4-Cyanophenyl)ethynyl]-4-biphenyloxy]ethoxy]ethoxy]carbonyl]-p-phenylene bis[p-[6-(acryloyloxy)hexyloxy]benzoate



5

Mp. (C-N) = 93°C; Clp (N-I) = 177°C;


This compound may be supercooled

Example 3

10 Preparation of Nematic LCP films


(i) A mixture of the following components in anisole was prepared:

60wt% of




15

20wt% of



20

10wt% of



and 10wt% of 1,4-butanediol diacrylate as a promoter of forming a polymer network.


5 Further 500ppm of 2,6-di-(t-butyl)-4-hydroxytoluene (BHT) inhibitor were added to this mixture in order to prevent untimely polymerisation. Polymerisation was started using 500ppm initiator such as Irgacure 369 (commercially available from Ciba Geigy, Basle, Switzerland). The mixture was stirred at room temperature and then spincoated on a glass plate having an orientation layer to form an LCP film of ca.

10 800nm in thickness. This film was dried at 50°C for 1 or 2 minutes and photopolymerised by irradiation with UV light for approximately 5 minutes at room temperature in a N<sub>2</sub> atmosphere using a mercury lamp.


The well oriented film shows the nematic mesophase at room temperature.

- 15 (ii) A mixture of the following components in Anisole was prepared according to the procedure of Example 1


60wt% of



20 20wt% of



10wt% of




5

and 10 wt% of 1,4-butanediol diacrylate (Aldrich).

This nematic film also shows a well oriented nematic mesophase at room temperature with a clearing point of about 85°C. In addition this film exhibits a tilt angle of about  
10 1° relative to the plane of the substrate, as shown by ellipsometric measurements.

# Claims

1. A compound of formula (I)



5 wherein

$G^1$  and  $G^2$  independently represent a polymerisable mesogenic residue;


X represents a group selected from  $-CH_2-$ ,  $-O-$ ,  $-CO-$ ,  $-COO-$ ,  $-OOC-$ ,  $-CONR'-$ ,  $-OCOO-$ ,  $-OCONR'$ ;

10

Sp represents a group of the formula  $-(CH_2)_p-$  in which p is an integer of 1 to 18 and in which one or two non adjacent  $-CH_2-$  groups are optionally replaced by  $-CH=CH-$ ; or in which one or two  $-CH_2-$  groups are optionally replaced by one or two groups selected from the group consisting of  $-O-$ ,  $-CO-$ ,  $-COO-$ ,  $-OOC-$ ,  $-CONR'-$ ,  $-OCOO-$ ,  $-OCONR'$  with the proviso that firstly the spacer group does not contain two adjacent heteroatoms and secondly when X is  $-CH_2-$ , p can also have a value of 0; and

15

M represents an achiral group of formula (II)




20

in which

A and B independently represent an optionally substituted six membered isocyclic or heterocyclic group or naphthalenediyl;

- C is selected from the group consisting of an optionally substituted five and six membered isocyclic or heterocyclic group or naphthalenediyl;  
 $n^1$  and  $n^2$  are 0 or 1 with the proviso that firstly  $1 \leq n^1 + n^2 \leq 2$  and secondly, when C is naphthalenediyl  $0 \leq n^1 + n^2 \leq 2$ ;
- 5  $Z^1$  is selected from the group consisting of -O-, -COO-, -OOC-, -CO-, -CONR'-, -NR'CO-, OCOO-, -OCONR'-, -NR'COO- and a single bond;  
 in which  
 R' is selected from the group consisting of hydrogen, a lower achiral alkyl group and a lower achiral alkenyl group;
- 10  $Z^2$  and  $Z^3$  are independently selected from the group consisting of single bond, -COO-, -OOC-, -CH<sub>2</sub>-CH<sub>2</sub>-, -CH<sub>2</sub>O-, -OCH<sub>2</sub>-, -CH=CH-, -C≡C-, -(CH<sub>2</sub>)<sub>4</sub>- and -(CH<sub>2</sub>)<sub>3</sub>O-; and
- 15  $R^1$  is selected from the group consisting of -CN, -COR, -COOR, -OCOR, -CONR'R, -NR'COR, OCOOR, -OCONR'R, -NR'COOR, -F, -Cl, -CF<sub>3</sub>, -OCF<sub>3</sub>, -OR and -R  
 in which  
 R is selected from the group consisting of hydrogen, an achiral C<sub>1-18</sub> alkyl group and an achiral C<sub>4-18</sub> alkenyl group with the double bond at  
 20 3-position or higher; and  
 R' is as defined above;
- with the proviso that at most one of the rings A, B and C is a naphthalenediyl group.
2. A compound according to Claim 1, in which G<sup>1</sup> and G<sup>2</sup> are the same.
  - 25 3. A compound according to Claim 1 or Claim 2, in which X is selected from -CH<sub>2</sub>-, -O-, -COO- and -OOC-.
  4. A compound according to any one of claims 1 to 3, in which the integer p of the group Sp has a value of from 1 to 12.
  5. A compound according to any one of the preceding claims, in which no more than  
 30 two -CH<sub>2</sub>- groups are replaced by -O-.

6. A compound according to any one of the preceding claims, in which no more than one  $-\text{CH}_2-$  group is replaced by a group selected from the group consisting of  $-\text{CH}=\text{CH}-$ ,  $-\text{CO}-$ ,  $-\text{COO}-$ ,  $-\text{OOC}-$ ,  $-\text{CONR}'$ ,  $-\text{OCOO}-$  and  $-\text{OCONR}'$ .
- 5 7. A compound according to any one of the preceding claims, in which groups the A and B comprising the group M are selected from the group consisting of 1,4-phenylene, pyridine-2,5-diyl, pyrimidine-2,5-diyl, trans-1,4-cyclohexylene or trans-1,3-dioxane-2,5-diyl, 1,4-naphthalenediyl and 2,6-naphthalenediyl.
8. A compound according to any one of the preceding claims, in which the group C comprising the group M is selected from furan-2,4-diyl, furan-2,5-diyl, 10 tetrahydrofuran-2,4-diyl, tetrahydrofuran-2,5-diyl, dioxolane-2,4-diyl, dioxolane-2,5-diyl, oxazole-2,4-diyl, oxazole-2,5-diyl, cyclopentane-1,3-diyl, cyclopentane-1,4-diyl, 1,4-phenylene, pyridine-2,5-diyl, pyrimidine-2,5-diyl, trans-1,4-cyclohexylene or dioxane-2,5-diyl, and 2,6-naphthalenediyl.
9. A compound according to any one of the preceding claims, in which the group  $Z^1$  15 comprising the achiral group M is selected from the group consisting of  $-\text{O}-$ ,  $-\text{COO}-$ ,  $-\text{OOC}-$  and a single bond.
10. A compound according to any one of the preceding claims, in which the groups  $Z^2$  and  $Z^3$  comprising the achiral group M are selected from the group consisting of  $-\text{COO}-$ ,  $-\text{OOC}-$ ,  $-\text{CH}_2\text{CH}_2-$ ,  $-\text{CH}_2\text{O}-$ ,  $-\text{OCH}_2-$ ,  $-\text{CH}=\text{CH}-$ ,  $-\text{C}\equiv\text{C}-$  and a single bond.
- 20 11. A compound according to any one of the preceding claims, in which the group  $R^1$  comprising the achiral group M is selected from the group consisting of  $-\text{CN}$ ,  $-\text{COOR}$ ,  $-\text{OCOR}$ , F, Cl,  $\text{CF}_3$ ,  $\text{OCF}_3$ , OR, R, in which R represents a  $\text{C}_{1-12}$  achiral alkyl, or  $\text{C}_{4-12}$  achiral alkenyl group, with the double bond at position 3- or higher, or hydrogen.
- 25 12. A compound according to any one of the preceding claims, in which the polymerisable mesogenic residues  $G^1$  and  $G^2$  are each independently represented by the group of formula III



wherein

5 D and E are independently selected from the group consisting of optionally substituted 1,4-phenylene, pyridine-2,5-diyl, pyrimidine-2,5-diyl, trans-1,4-cyclohexylene and trans-1,3-dioxane-2,5-diyl;

m is 1 or 0,

10  $Z^4$  and  $Z^5$  are independently selected from the group consisting of a single bond, -COO-, -OOC-, -CH<sub>2</sub>-CH<sub>2</sub>-, -CH<sub>2</sub>O-, -OCH<sub>2</sub>-, -CH=CH-, -C≡C-, -(CH<sub>2</sub>)<sub>4</sub>- and -(CH<sub>2</sub>)<sub>3</sub>O-;

15  $Z^6$  represent a group of formula -(CH<sub>2</sub>)<sub>p</sub>X- in which p is an integer having a value of 1 to 18 and X is as defined in Claim 1, and in which one or two non adjacent -CH<sub>2</sub>- groups may be optionally replaced by -CH=CH- or in which one or two -CH<sub>2</sub>- groups may be replaced by one or two additional linking groups X with the proviso that firstly the group  $Z^6$  does not contain two adjacent heteroatoms and secondly  
20 when X is -CH<sub>2</sub>, p can also have a value of 0


$R^2$  represents a polymerisable group selected from the group consisting of  
CH<sub>2</sub>=C(Ph)-, CH<sub>2</sub>=CW-COO-, CH<sub>2</sub>=CH-COO-Ph-,  
CH<sub>2</sub>=CW-CO-NH-, CH<sub>2</sub>=CH-O-, CH<sub>2</sub>=CH-OOC-, Ph-CH=CH-,  
25 CH<sub>2</sub>=CH-Ph-, CH<sub>2</sub>=CH-Ph-O-, R<sup>3</sup>-Ph-CH=CH-COO-,  
R<sup>3</sup>-OOC-CH=CH-Ph-O- and 2-W-epoxyethyl  
in which

W represents H, Cl, Ph or a lower alkyl,




$R^3$  represents a lower alkyl with the proviso that when  $R^3$  is attached to a phenylene group (-Ph-) it may also represent hydrogen or a lower alkoxy.

13. A compound according to Claim 12, in which the groups D and E are selected from optionally substituted 1,4-phenylene and 1,4-cyclohexylene rings.
14. A compound according to Claim 12 or Claim 13, in which  $Z^4$  and  $Z^5$  are selected from the group consisting of a single bond, -COO-, -OOC-, -CH<sub>2</sub>-CH<sub>2</sub>-, -CH<sub>2</sub>O-, -OCH<sub>2</sub>-, -CH=CH- and -C≡C-.
15. A compound according to any one of claims 12 to 14, in which the group  $R^2$  is selected from the group consisting of CH<sub>2</sub>=CW-COO- and CH<sub>2</sub>=CH-O-.
16. A LCP mixture comprising a compound of formula (I)



wherein

- $G^1$  and  $G^2$  independently represent a polymerisable mesogenic residue;
- X represents a group selected from -CH<sub>2</sub>-, -O-, -CO-, -COO-, -OOC-, -CONR'-, -OCOO-, -OCONR';
- Sp represents a group of the formula -(CH<sub>2</sub>)<sub>p</sub>- in which p is an integer of 1 to 18 and in which one or two non adjacent -CH<sub>2</sub>- groups are optionally replaced by -CH=CH-; or in which one or two -CH<sub>2</sub>- groups are optionally replaced by one or two groups selected from the group consisting of -O-, -CO-, -COO-, -OOC-, -CONR'-, -OCOO-, -OCONR' with the proviso that firstly the spacer group does not contain two adjacent heteroatoms and secondly when X is -CH<sub>2</sub>-, p can also have a value of 0; and
- M represents an achiral group of formula (II)



in which

A and B independently represent an optionally substituted six membered isocyclic or heterocyclic group or naphthalenediyl;

C is selected from the group consisting of an optionally substituted five and six membered isocyclic or heterocyclic group or naphthalenediyl;

$n^1$  and  $n^2$  are 0 or 1 with the proviso that firstly  $1 \leq n^1 + n^2 \leq 2$  and secondly, when C is naphthalenediyl  $0 \leq n^1 + n^2 \leq 2$ ;

$Z^1$  is selected from the group consisting of -O-, -COO-, -OOC-, -CO-, -CONR'-, -NR'CO-, OCOO-, -OCONR'-, -NR'COO- and a single bond;

in which

$R'$  is selected from the group consisting of hydrogen, a lower achiral alkyl group and a lower achiral alkenyl group;

$Z^2$  and  $Z^3$  are independently selected from the group consisting of single bond, -COO-, -OOC-, -CH<sub>2</sub>-CH<sub>2</sub>-, -CH<sub>2</sub>O-, -OCH<sub>2</sub>-, -CH=CH-, -C≡C-, -(CH<sub>2</sub>)<sub>4</sub>- and -(CH<sub>2</sub>)<sub>3</sub>O-; and

$R^1$  is selected from the group consisting of -CN, -COR, -COOR, -OCOR, -CONR'R, -NR'COR, OCOOR, -OCONR'R, -NR'COOR, -F, -Cl, -CF<sub>3</sub>, -OCF<sub>3</sub>, -OR and -R

in which

R is selected from the group consisting of hydrogen, an achiral C<sub>1-18</sub> alkyl and an achiral C<sub>4-18</sub> alkenyl group with the double bond at 3-position or higher; and

$R'$  is as defined above;

with the proviso that at most one of the rings A, B and C is a naphthalenediyl group and one or more additional suitable components.

17. A LCP network comprising a compound according to any one of Claims 1 to 15 or a mixture according to Claim 16 in cross-linked or polymerised form.
- 5 18. Use of a compound according to any one of claims 1 to 15, or a mixture according to Claim 16, in the manufacture of an optical or an electro-optical device.
19. An optical or electro-optical device including a compound according to any one of claims 1 to 15, a mixture according to Claim 16 or a network according to Claim 17.

# INTERNATIONAL SEARCH REPORT

In ternational Application No

PCT/IB 00/00158

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C07C69/92 C09K19/20 C09K19/34 C09K19/32 C09K19/38

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 748 852 A (HOFFMANN LA ROCHE) 18 December 1996 (1996-12-18) page 6, line 34 -page 7, line 30 page 8 claims 8-13	1-19
Y,P	WO 99 64924 A (SCHADT MARTIN ;ROLIC AG (CH); SEIBERLE HUBERT (DE)) 16 December 1999 (1999-12-16) page 8, line 1 - line 15	1-19
Y,P	WO 99 37735 A (BUHECKER RICHARD ;ROLIC AG (CH); BENECKE CARSTEN (DE); MARCK GUY) 29 July 1999 (1999-07-29) page 9, line 14 -page 10, line 25	1-19
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

19 April 2000

Date of mailing of the international search report

11. 05. 00

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Boulon, A

Form PCT/ISA/210 (second sheet) (July 1992)

BEST AVAILABLE COPY

page 1 of 2

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/IB 00/00158

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y,P	<p>WO 00 04110 A (CHERKAoui ZOUBAIR ;ROLIC AG (CH); BENECKE CARSTEN (DE)) 27 January 2000 (2000-01-27) examples 4,5</p> <p>-----</p>	1-19

# INTERNATIONAL SEARCH REPORT

I national application No.  
PCT/IB 00/00158

## Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:  
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☒ Claims Nos.:  
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:  
see FURTHER INFORMATION sheet PCT/ISA/210
3. ☐ Claims Nos.:  
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

## Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

## Continuation of Box I.2

Present claims 1-19 relate to an extremely large number of possible compounds. Support within the meaning of Article 6 PCT and/or disclosure within the meaning of Article 5 PCT is to be found, however, for only a very small proportion of the compounds claimed. In the present case, the claims so lack support, and the application so lacks disclosure, that a meaningful search over the whole of the claimed scope is impossible. Consequently, the search has been carried out for those parts of the claims which appear to be supported and disclosed, namely those parts relating to the compounds prepared in the examples 1-3 and closely related homologous compounds .

The applicant's attention is drawn to the fact that claims relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as IPEA is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure."

BEST AVAILABLE COPY

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. .ational Application No

PCT/IB 00/00158

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0748852 A	18-12-1996	CN 1143665 A JP 8333320 A SG 63652 A US 5707544 A	26-02-1997 17-12-1996 30-03-1999 13-01-1998
WO 9964924 A	16-12-1999	NONE	
WO 9937735 A	29-07-1999	NONE	
WO 0004110 A	27-01-2000	NONE	